

MIDALLOY ER80S-D2 WELDING WIRE

CLASSIFICATION

- AWS 5.28 Class ER80S-D2 / ASME SFA 5.28 Class ER80S-D2

DESCRIPTION

- MIDALLOY ER80S-D2 welding wire is a copper-coated wire, used for GMAW and GTAW welding.

APPLICATION

- MIDALLOY ER80S-D2 welding wire is designed for the gas metal arc welding and gas tungsten arc welding when moderately high strength and good sub-zero toughness is needed in the PWHT condition.
- Preheating and interpass temperatures of not less than 300°F must be used during welding.

TYPICAL CHEMISTRY

C	Mn	Si	Cr	Mo	P	S	Cu
.09	1.75	.70	.05	.47	.010	.012	.15

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	84,000 PSI
YIELD STRENGTH	71,500 PSI
ELONGATION	19%
IMPACT STRENGTH @ -20°F	35 ft. lbs.

Note: Mechanical Properties of welds are greatly influenced by preheat inter-pass temperature, heat input, and PWHT.

RECOMMENDED WELDING PARAMETERS

PROCESS	DIA. OF WIRE	AMPERAGE	VOLTAGE	GAS/FLUX
GTAW (TIG)	1/16"	50-120	7-13	Ar
	3/32"	120-200	10-16	Ar
	1/8"	150-220	12-18	Ar
GMAW (MIG) SHORT ARC	.035"	90-160	14-20	CO ₂
	.045"	120-200	16-20	CO ₂ or 75 Ar / 25 CO ₂
	1/16"	-	-	CO ₂ or 75 Ar / 25 CO ₂
GMAW (MIG) SPRAY TRANSFER	.035"	180-230	25-28	98 Ar / 2 O ₂
	.045"	250-350	25-30	75 Ar / 25 CO ₂
	1/16"	280-400	26-36	75 Ar / 25 CO ₂

STANDARD PACKAGE

- TIG 50 lb. carton
- MIG 33 lb. spool

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

