

MIDALLOY ER80S-Ni 1 WELDING WIRE

CLASSIFICATION

- AWS A5.28 Class ER80S-Ni1 / ASME SFA 5.28 Class ER80S-Ni1 (UNS K11260) and EN10204

DESCRIPTION

- MIDALLOY ER80S-Ni1 is a copper-coated wire, used for GMAW and GTAW welding.
- F#6 A#10

APPLICATION

- MIDALLOY ER80S-Ni1 welding wire is used for Tig root passes or Tig & Mig joining of carbon manganese high strength steels, requiring good toughness at temperature as low as -40°F.

TYPICAL CHEMISTRY

C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu
.11	1.02	.58	.012	.010	.92	.04	.01	.002	.14

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	87,000 PSI (599 KPA)
YIELD STRENGTH	73,950 PSI (509 KPA)
ELONGATION IN 2"	25%
CHARPY IMPACT @ -40°F	44 ft. lbs. Average 75%Ar/25%CO ₂ 30 ft. lbs. Average 100% CO ₂

RECOMMENDED WELDING PARAMETERS

PROCESS	DIA. OF WIRE	AMPERAGE	VOLTAGE	GAS/FLUX
GTAW	1/16"	50-120	7-13	Ar
	3/32"	120-200	10-16	Ar
	1/8"	150-220	12-18	Ar
GMAW (MIG) SHORT ARC	.035"	90-160	14-20	CO ₂
	.045"	120-200	16-20	CO ₂ or 75 Ar/25 CO ₂
	1/16"	-	-	CO ₂ or 75 Ar/25 CO ₂
GMAW (MIG) SPRAY TRANSFER	.035"	180-230	25-28	98 Ar/2 O ₂
	.045"	250-350	25-30	75 Ar/25 CO ₂
	1/16"	280-400	26-36	75 Ar/25 CO ₂

STANDARD PACKAGING

- TIG 50 lb. carton
- MIG 33 lb. spool

6/4/10

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
630 Axminister Drive
St. Louis, MO 63026 • 636-349-6000 • 800-776-3300
Fax 636-349-2240

