

MIDALLOY ER90S-B9 / EB9 WELDING WIRE

CLASSIFICATION

- GTAW & GMAW AWS 5.28 Class ER90S-B9 / ASME SFA 5.28 ER90S-B9
SAW AWS 5.23 Class EB9 / ASME SFA 5.23

DESCRIPTION

- Copper-coated welding wire for joining 9 CrMo modified steels with small additions of Vanadium and Niobium such as A213-T91 tubes, A335-P91 pipe, and A387 Grade 91 plates and A182 F91 forgings.

APPLICATIONS

- Designed for improved long term creep properties in heavy wall components such as headers, main steam piping and turbine rotors in fossil fueled power-generating plants.

TYPICAL CHEMISTRY (GTAW)

C	Mn	Si	S	Ni	Cr	Mo	V	Al	Cu	Nb	N
.09	.59	.20	.002	.63	8.93	.87	.21	.006	.05	.07	.045

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	112,600 PSI
YIELD STRENGTH	100,700 PSI
ELONGATION IN 2"	17.2 %
CHARPY IMPACT **	40 ft. lbs.

** @1400° PWHT for 2 hours

RECOMMENDED WELDING PARAMETERS

PROCESS	DIA. OF WIRE	AMPERAGE	VOLTAGE	GAS/FLUX
GTAW (TIG)	1/16"	50-120	7-13	Ar
	3/32"	120-200	10-16	Ar
	1/8"	150-220	12-18	Ar
GMAW (MIG) SHORT ARC	.035"	90-160	14-20	CO ₂
	.045"	120-200	16-20	CO ₂
	1/16"	-	-	-
GMAW (MIG) SPRAY	.035"	180-230	25-28	Ar / CO ₂
	.045"	250-350	25-30	Ar / CO ₂
	1/16"	280-400	26-36	Ar / CO ₂
SUBMERGED ARC	3/32"	250-340	26-34	MARATHON 543
	1/8"	350-480	26-34	MARATHON 543
Travel Speed – 8-15 IPM		Stickout – 3/4" Avg.		

STANDARD PACKAGING

- TIG 50 lb. carton
- MIG 33 lb. Spool 55 lb.
- SUB-ARC EB9 Sub-Arc Wire

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.