

MIDALLOY MASTERCOR ENiCrCoMo-1 AP FLUX-CORED WIRE

CLASSIFICATION

- Chemistry conforms to AWS/SFA 5.34. The AWS classification for this flux-cored wire is ENiCrCoMo-1T1-4 for Argon-CO₂ shielding gas and ENiCrCoMo-1T1-1 for 100% CO₂.

DESCRIPTION

- Midalloy Mastercor ENiCrCoMo-1 AP nickel alloy wire for welding in the flat and horizontal positions.
- UNS# W86117
- ISO# TNi6117-xy

APPLICATIONS

- Midalloy Mastercor ENiCrCoMo-1 AP is used for welding chromium-cobalt-molybdenum alloys such as UNS number N06617 as well as cast alloys HK-40, HP, and HP modified.
- This wire is used for overlay, cladding where similar alloy is required.
- Weld metal provides optimum strength and oxidation resistance above 1500°F.

TYPICAL CHEMISTRY

C	Mn	Fe	P	S	Si	Cu	Ni	Co	Cr	Cb+Ta	Mo	Other
.08	.95	.40	.012	.004	.38	.04	54.3	11.4	22.79	.05	9.25	<.50

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	90,000 PSI
ELONGATION	25%

WELDING PARAMETERS

SIZE	VOLTS	AMPS	STICK-OUT	SHIELDING GAS
1/16"	26-28	190-230	1/2"	75Ar/25CO ₂

STANDARD PACKAGING

- 33 LB. SPOOL

12-1-08

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

