

MIDALLOY NI-MAX 122 COATED ELECTRODE

CLASSIFICATION

- AWS/SFA 5.11 Class ENiCrMo-10/ASME SFA 5.11 Class ENiCrMo-10 ASME SEC IX, F44

DESCRIPTION

- Midalloy NI-MAX 122 coated electrode is an all position coated electrode used for joining alloys listed under UNS# N06022. These include nickel-chromium-molybdenum base metals such as ASTM F574, B619, B622, and B626. Also used for overlay where a similar composition is required on the clad side.
- UNS# W86022
- ISO 14172 comparison classification ENi6022
- These electrodes can also be used in dissimilar applications involving nickel-chromium-molybdenum alloys welded to stainless steels containing molybdenum.

APPLICATION

- NI-MAX 122 is used for a wide range of applications in the chemical, power, petroleum, and marine industries.
- NI-MAX 122 offers excellent corrosion resistance in both oxidizing and reducing media used for chemical processing.
- NI-MAX 122 offers an outstanding resistance to stress corrosion cracking, pitting, and crevice corrosion.

TYPICAL CHEMISTRY

C	Mn	Fe	P	S	Si	Cu	Ni	Co	Cr	Mo	V	W
.015	.33	2.7	.010	.006	.15	.05	57.75	.01	21.29	14.0	.01	3.24

TYPICAL WELDING PROPERTIES

TENSILE STRENGTH	114,000 PSI
YIELD STRENGTH	79,000 PSI
ELONGATION IN 2"	36%

RECOMMENDED WELDING PARAMETERS

DIAMETER	3/32"	1/8"	5/32"	3/16"
PROCESS	SMAW	SMAW	SMAW	SMAW
VOLTAGE	24-28	26-30	28-32	28-32
AMPERAGE FLAT	70-85	65-100	110-140	120-160
AMPERAGE VERTICAL/OVERHEAD	65-75	65-90	100-120	110-130

STANDARD PACKAGING

- 3/32" – 8 lb. can, 48 lb. carton
- 1/8", 5/32", 3/16" – 10 lb. can, 60 lb. carton

12-1-08

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

