

## MIDALLOY NI-MAX A COATED ELECTRODE

### CLASSIFICATION

- AWS/SFA 5.11 Class ENiCrFe-2/ASME SFA 5.11 Class ENiCrFe-2 ASME SEC IX, F43

### DESCRIPTION

- Midalloy Ni-MAX A coated electrode is an all-position, coated electrode used for joining alloys listed under the UNS numbers N06600 and N08800 to themselves.
- UNS# W86133
- ISO 14172 comparison ENi6133
- Ni-MAX A can also be used to weld these same alloys to mild, low alloy, and stainless steels.
- Used for cryogenic applications involving 3%-9% nickel.

### APPLICATION

- Ni-MAX A is widely used for general maintenance welding of high nickel alloys to themselves for equipment exposed to difficult service conditions. These applications include furnace equipment and petrochemical plants up to approximately 1,000°C.
- Ni-MAX A can also be used for dissimilar welds of nickel alloys to mild steel or stainless steel up to approximately 600°C. These welds can generally be done without preheat (avoid free machining grades). Stress relief is acceptable if necessary, and the transition welds for high temperature service have good structural stability.

### TYPICAL CHEMISTRY

C	Mn	Fe	P	S	Si	Cu	Ni	Cr	Cb+Ta	Mo	Others
.04	1.75	9.0	.012	.013	.32	.02	70.0	15.5	1.25	1.5	<0.05

### TYPICAL MECHANICAL PROPERTIES

Tensile Strength	89,000 PSI
Yield Strength	72,000 PSI
Elongation	36%

### RECOMMENDED WELDING PARAMETERS

Diameter	3/32"	1/8"	5/32"	3/16"
Process	SMAW	SMAW	SMAW	SMAW
Voltage	24-28	26-30	28-32	28-32
Amperage Flat	70-85	65-100	110-140	120-160
Amperage Vertical/Overhead	65-75	65-90	100-120	110-130

### STANDARD PACKAGING

- 3/32" – 8 lb. Can, 48 lb. Carton
- 1/8", 5/32", 3/16" – 10 lb. Can, 60 lb. Carton

12-1-08

*The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.*

Office and Corporate Warehouse  
 630 Axminister Drive  
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300  
 Fax 636-349-2240

