

MIDALLOY ER308L BARE WIRE

CLASSIFICATION

- AWS 5.9 Class ER308L / ASME SFA 5.9 Class ER308L
- UNS# S30880 A#8 F#6

DESCRIPTION

- MIDALLOY ER308L stainless steel wire is used for GMAW, GTAW and SAW welding.

APPLICATIONS

- MIDALLOY ER308L is used to weld metals with similar composition; such as 304L (UNS S30403), in wrought and cast forms. This product is melted to reduce levels of carbon, phosphorus, and sulfur to reduce micro-fissuring.

TYPICAL CHEMISTRY

C	Si	Cr	Mn	P	Cu	S	N	Mo	Ni
.015	.48	20	1.85	.015	<.20	.010	.06	<.50	10.1

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	83,500 PSI
YIELD STRENGTH	56,000 PSI
ELONGATION IN 2"	40%
CHARPY IMPACT @-320° F	45 FT-LBS

RECOMMENDED WELDING PARAMETERS

PROCESS	DIAMETER	VOLTAGE	AMPERAGE	GAS/FLUX*
TIG (GTAW)	1/16"	14-18	90-130	100% Ar
	3/32"	15-20	120-175	100% Ar
	1/8"	15-20	150-220	100% Ar
MIG (GMAW)	.035" SHORT ARC	16-26	70-160	69%Ar-30%He-1%O ₂
	.035" SPRAY ARC	26-31	150-230	92%Ar-8%Co ₂ or
	.045" SPRAY ARC	28-32	180-280	98%Ar-2%O ₂
SUB ARC (SAW)	3/32"	28-30	275-350	Record IN or
	1/8"	29-32	350-450	Record IND 24

PACKAGING

- TIG 10 lb. tube/60 lb. carton
- MIG 30 lb. spool
- SUB-ARC 60 lb. coil

10/8/09

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

Midalloy