

## MIDALLOY MASTERCOR™ E308LT0-1/4 F & H FLUX-CORED WIRE

### CLASSIFICATION

- AWS 5.22 Class E308LT0-1 and E308LT0-4 / ASME SFA 5.22 Class E308LT0-1 and E308LT0-4 flux cored wire.
- UNS# W30835 A# 8 F# 6

### DESCRIPTION

- MIDALLOY Mastercor™ E308LT0-1/4 is a gas shielded flux-cored wire designed for flat and horizontal welding and can be used with 75% Argon 25% CO<sub>2</sub> or 100% CO<sub>2</sub> shielding gas.

### APPLICATIONS

- MIDALLOY Mastercor™ E308LT0-1/4 is used for welding stainless steel grades 301, 302, 304L, 308, and 308L for various applications for the chemical, paper, pharmaceutical, textile, food and other industries.

### TYPICAL CHEMISTRY (%)

C	Mn	Si	Cr	Ni	Mo	P	S	N
0.03	1.22	.63	20.10	10.40	.20	.015	.015	.05

Controlled Ferrite WRC 92: 8-12 FN

### TYPICAL MECHANICAL PROPERTIES\*

TENSILE STRENGTH	82,300 PSI
YIELD STRENGTH	58,700 PSI
ELONGATION IN 2"	38%

Note: Mechanical properties shown using 100% CO<sub>2</sub> shielding gas

### OPTIMUM TYPICAL WELDING PARAMETERS (using 100% CO<sub>2</sub> shielding gas)

DIAMETER	AMPERAGE	VOLTAGE	WFS (IPM)	STICK/OUT
.045"	170-200	27-29	335-440	5/8" / 3/4"
1/16"	210-270	28-31	235-345	3/4" / 1"

Note: Lower volts by 2 volts when using 75AR/25CO<sub>2</sub>

### STANDARD PACKAGING

- 33 lb. spool

12/29/08

*The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.*

Office and Corporate Warehouse  
 630 Axminister Drive  
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300  
 Fax 636-349-2240

