

MIDALLOY MASTERCOR™ E309LT0-1/4 F & H FLUX-CORED WIRE

CLASSIFICATION

- AWS 5.22 Class E309LT0-1 and E309LT0-4 / ASME SFA 5.22 Class E309LT0-1 and E309LT0-4 flux cored wire.
- UNS# W30935 A# 8 F# 6

DESCRIPTION

- MIDALLOY Mastercor™ E309LT0-1/4 is a gas shielded flux-cored wire designed for flat and horizontal welding and can be used with 75% Argon 25% CO₂ or 100% CO₂ shielding gas.

APPLICATIONS

- MIDALLOY Mastercor™ E309LT0-1/4 is used for welding type 309 stainless steel to itself.
- Can also be used to join carbon and low alloy steels to austenitic stainless steels.
- Can be used to weld 304 clad sheets and for first layer of cladding carbon steel.

TYPICAL CHEMISTRY (%)

C	Mn	Si	Cr	Ni	Mo	P	S	N	Cu
0.03	1.0	.67	24.60	13.2	1.0	.015	.006	.05	.12

Controlled Ferrite WRC 92: 19 FN

TYPICAL MECHANICAL PROPERTIES*

TENSILE STRENGTH	88,000 PSI
YIELD STRENGTH	69,200 PSI
ELONGATION IN 2"	32%

Note: Mechanical properties shown using 100% CO₂ shielding gas

OPTIMUM TYPICAL WELDING PARAMETERS (using 100% CO₂ shielding gas)

DIAMETER	AMPERAGE	VOLTAGE	WFS (IPM)	STICK/OUT
.045"	170-200	27-29	335-440	5/8" / 3/4"
1/16"	210-270	28-31	235-345	3/4" / 1"

Note: Lower volts by 2 volts when using 75AR/25CO₂

STANDARD PACKAGING

- 33 lb. spool

1/6/09

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

