

MIDALLOY CHROMAX E316L-16 COATED ELECTRODE

CLASSIFICATION

- AWS 5.4 Class E316L-16 ASME SFA 5.4 Class E316L-16 ASME Sec. IX, F4, A8

DESCRIPTION

- MIDALLOY CHROMAX E316L-16 is AC-DC titania coated electrode
- UNS W31613
- ISO 3518B comparison classification ES316L

APPLICATION

- For welding or repairing alloy 316L
- Overlay of carbon and low alloy steels to achieve a Cr-Ni Mo stainless steel (E309L-16 and E316L-16).
- Deposit composition of E316L has Chromium, Nickel and Molybdenum for better corrosion resistance than E3-8L-16
- Low Ferrite E316L-16 has been used for low temperature (cryogenic) service.

TYPICAL CHEMISTRY

C	Cr	Ni	Mo	Mn	Si	P	S	Cu	N
.03	19.5	13.3	2.75	1.7	.50	.020	.010	.10	.06

FERRITE CONTENT 5-12 WRC 1992

TYPICAL MECHANICAL PROPERTIES (as welded all weld metal)

TENSILE STRENGTH	77,500 PSI
YIELD STRENGTH	60,500 PSI
ELONGATION IN 2"	38%

RECOMMENDED WELDING PARAMETERS

DIAMETER	AMPERAGE	
	FLAT	VERTICAL & OVERHEAD
3/32"	70-85	65-75
1/8"	85-110	80-90
5/32"	110-140	100-120
3/16"	120-160	110-130

STANDARD PACKAGING

3/32" - 8 lb. can, 48 lb. Carton
 1/8", 5/32", 3/16" - 10 lb. Can, 60 lb. Carton

7/1/09

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminster Drive
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

