

MIDALLOY ERNi-1 (FM61) BARE WIRE

CLASSIFICATION

- AWS 5.14 Class ERNi-1 / ASME SFA 5.14 Class ERNi-1

DESCRIPTION

- MIDALLOY ERNi-1 nickel alloy bare wire is used for GMAW, GTAW, and SAW welding.

APPLICATIONS

- MIDALLOY ERNi-1 nickel alloy bare wire is used for joining nickel 200 and nickel 201. This includes ASTM grades such as B160 – B163, B725 and B730.
- This alloy is useful in a variety of dissimilar applications between nickel alloys to stainless or ferritic steels.
- This versatile alloy is also used for overlaying carbon steel and in repairing cast iron castings.

TYPICAL CHEMISTRY

C	Mn	Si	Fe	S	P	Cu	Al	Ti	Ni
.03	.50	.54	.30	.003	.006	.01	.03	2.46	96.1

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	65,000 PSI
YIELD STRENGTH	37,000 PSI
ELONGATION	27%

RECOMMENDED WELDING PARAMETERS

(See attached)

STANDARD PACKAGING

- TIG 10 lb. tube / 60 lb. carton
- MIG 30 lb. spool
- SUB-ARC 60 lb. coil

10-15-2010

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 St. Louis, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240



TYPICAL WELDING PARAMETERS FOR NICKEL ALLOYS

GMAW (SHORT CIRCUITING MODE)

WIRE DIA.	AMPERAGE	VOLTAGE	WIRE SPEED, IN./MIN.	JOINT THICKNESS IN.	GAS
.035"	70-90	18-20	150-200	.050-3/16	75Ar/25He
	70-90	17-20	150-200	.050-3/16	90He/7.5Ar/2.5Co2
	70-90	17-20	150-200	.050-3/16	69Ar/30He/1Co2
.045"	75-160	19-22	175-225	1/8-3/4	75Ar/25He
	75-160	19-22	175-225	1/8-3/4	90He/7.5Ar/2.5Co2
	75-160	18-22	175-225	1/8-3/4	69Ar/30He/1Co2

GMAW (SPRAY TRANSFER MODE)

.045"	190-250	30-32	300-350	3/8 and UP	100Ar
-------	---------	-------	---------	------------	-------

GMAW (PULSED CURRENT MODE)

.045" peak	120-150 250-300	18-20	175-225	1/8-3/4	75Ar/25He
peak	120-150 250-300	18-20	175-225	1/8-3/4	69Ar/30He/1Co2

GTAW (TIG)

JOINT THICKNESS IN.	TUNGSTEN ELECTRODE DIA. IN.	FILLER WIRE DIA. IN.	AMPERAGE	VOLTAGE	GAS
.030 to 1/16	1/16	1/16	35-60	9-12	100Ar
1/16 to 1/8	1/16 to 3/32	1/16 or 3/32	50-95	9-12	100Ar
1/8 to 1/4	3/32 or 1/8	3/32 or 1/8	75-150	10-13	100Ar
1/4 and up	3/32 or 1/8	3/32 or 1/8	95-200	10-13	100Ar

SAW (SUBMERGED ARC)

WIRE DIA.	AMPERAGE	VOLTAGE	
3/32"	275-350	28-30	Suitable flux
1/8"	350-450	29-32	Suitable flux

SMAW (COATED ELECTRODES)

DIA. & LENGTH	AMPERAGE/FLAT	AMPERAGE/ VERT. & OVERHEAD	VOLTAGE
3/32" x 12"	70-85	65-75	24-28
1/8" x 14"	85-110	80-90	26-30
5/32" x 14"	110-140	100-120	28-32
3/16" x 14"	120-160	110-130	28-32

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.