

MIDALLOY ER110S-1 WELDING WIRE

CLASSIFICATION

- AWS 5.28 Class ER110S-1 / ASME SFA 5.28 Class ER110S-1. Ref UNS K21015

DESCRIPTION

- MIDALLOY ER110S-1 is a low alloy, bare welding wire suited for MIG or TIG welding.
 - A#2 F#6

APPLICATIONS

- MIDALLOY ER110S-1 is used to weld HY80 and other similar steels with over 100 KSI tensile
- Welds exhibit high strength as well as low temperature toughness down to -60°F.

TYPICAL CHEMISTRY

C	Mn	Si	P	S	Ni	Cr	Mo	V	Ti	Zr	Al	Cu
0.08	1.6	0.45	0.005	0.005	2.2	0.2	0.3	0.03	0.01	.001	0.01	.15

TYPICAL AS WELDED MECHANICAL PROPERTIES

TENSILE STRENGTH	114,000 PSI
YIELD STRENGTH	98,000 PSI
ELONGATION IN 2"	16%
CHARPY V NOTCH @ -60°F	60 ft. lbs.

WELDING PARAMETERS (GMAW)

DIA.	SPRAY TRANSFER			SHORT ARC		
	AMPS.	VOLTS	GAS	AMPS.	VOLTS	GAS
.035"	160-200	28 – 32	98 Ar/2 O ₂	100-140	22 - 25	100% CO ₂
.045"	180-220	30 - 34	75 Ar/25 CO ₂	120-150	23 - 26	75 Ar/25 CO ₂

OTHER INFORMATION

- Mechanical properties are greatly influenced by preheat, interpass temperature, and post weld heat treatment.

STANDARD PACKAGING

- MIG 33 lb. Spool
- TIG 10 lb. Tubes / 60 lb. Carton

10/17/13

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminster Drive
 St. Louis, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

Midalloy