

MIDALLOY ER120S-G WELDING WIRE

CLASSIFICATION

- AWS 5.28 Class ER120S-G / ASME SFA 5.28 Class ER120S-G, EN 12534 G894MMn4Ni2CrMo

DESCRIPTION

- MIDALLOY ER120S-G is a medium alloy, bare welding wire suited for MIG or TIG welding.

APPLICATIONS

- MIDALLOY ER120S-G is used to weld HY-100 and other similar steels.
- Welds exhibit high strength as well as low temperature toughness.
- Good resistance to cold cracking.
- Used for joining large vehicle and crane manufacturing.
- High strength pressure vessels and some heat treatable steels.

TYPICAL CHEMISTRY

C	Mn	Si	P	S	Ni	Cr	Mo	V	Ti	Zr	Al	Cu
.09	1.9	.80	.005	.005	2.15	.35	.55	.004	.08	.012	.01	.13

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	137,785 PSI
YIELD STRENGTH	129,080 PSI
ELONGATION IN 2"	16%
CHARPY V NOTCH @ -40°C	66 Joules

WELDING PARAMETERS (GMAW)

DIA.	SPRAY TRANSFER			SHORT ARC		
	AMPS.	VOLTS	GAS	AMPS.	VOLTS	GAS
.035"	160-200	28 - 32	98 Ar/2 O ₂	100-140	22 - 25	100% CO ₂
.045"	180-220	30 - 34	75 Ar/25 CO ₂	120-150	23 - 26	75 Ar/25 CO ₂

OTHER INFORMATION

- Mechanical properties are greatly influenced by preheat, interpass temperature, and post weld heat treatment.
- Approvals: TÜV DB

STANDARD PACKAGING

- 33 lb. Spool
- 50 lb. bulk box

10/17/13

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 St. Louis, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

