MIDALLOY ER70S-B2L (formerly ER80S-B2L) WELDING WIRE

CLASSIFICATION

- AWS 5.28:2005 Class ER70S-B2L / ASME SEA 5.28 Class ER70S-B2L
- AWS 5.28:1979 Class ER80S-B2L
- UNS #K20500

DESCRIPTION

MIDALLOY ER70S-B2L welding wire is a bare wire, used for GMAW and GTAW welding.

APPLICATION

- MIDALLOY ER70S-B2L a low carbon content variation (0.05%C max.) of ER80S-B2. Midalloy ER70S-B2L welding wire is designed for the welding of 11/4 Cr / 1/2 Mo steel that require a lower as-welded hardness.
- Normal applications include framework on transportation equipment (i.e. auto frames, mountain bikes etc).
- Structural supports and ductwork which are used for higher temperature service than mild steels.
- Controlling preheating from 275°F to 325°F and interpass temperatures of 750°F during welding followed by slow cooling to room temperature is beneficial to keep ductility.
- The as-welded filler metal deposit exhibits a lower strength and hardness and may not require PWHT.
- Midalloy ER70S-B2L elevated temperature creep rupture values are not as high as ER80S-B2.

TYPICAL CHEMISTRY

С	Mn	Si	Cr	Мо	Р	S	Cu
.04	.55	.48	1.35	.55	.012	.006	.15

TYPICAL MECHANICAL PROPERTIES	AS WELDED*	PWHT 1150°F**
TENSILE STRENGTH	85,000 PSI	75,000 PSI MIN
YIELD STRENGTH	71,500 PSI	58,000 PSI MIN
ELONGATION	18%	19%
HARDNESS	23 Rc	85Rb to 20 Rc

^{*}As welded with a preheat of 300°F and interpass of 750°F

RECOMMENDED WELDING PARAMETERS

PROCESS	DIA. OF WIRE	AMPERAGE	VOLTAGE	GAS/FLUX
	1/16"	50-120	7-13	Ar
GTAW (TIG)	3/32"	120-200	10-16	Ar
	1/8"	150-220	12-18	Ar
GMAW (MIG) SHORT ARC	.035"	90-160	14-20	CO_2
	.045"	120-200	16-20	CO ₂ or 75 Ar / 25 CO ₂
SHORT ARC	1/16"	-	-	CO ₂ or 75 Ar / 25 CO ₂
GMAW (MIG)	.035"	180-230	25-28	98 Ar / 2 O ₂
SPRAY	.045"	250-350	25-30	75 Ar / 25 CO ₂
TRANSFER	1/16"	280-400	26-36	75 Ar / 25 CO ₂

STANDARD PACKAGE

TIG 50 lb. cartonMIG 33 lb. spool

10/17/13

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.



^{**}Post weld heat treatment between 1150°F for one hour.