

MIDALLOY CHROMAX E317L-16 COATED ELECTRODE

CLASSIFICATION

- AWS 5.4 Class E317L-16 ASME SFA 5.4 Class E317L-16 ASME Sec. IX, F4, A8

DESCRIPTION

- MIDALLOY CHROMAX E317L-16/E317L-16 is AC-DC titania coated electrode
- UNS W31713
- ISO 3518B comparison classification ES317L

APPLICATION

- For welding or repairing alloy 317L
- Overlay of carbon and low alloy steels to achieve a Cr-Ni Mo stainless steel (316L).
- Deposit composition of E317L has 1% more Chromium, Nickel and Molybdenum than E316L

TYPICAL CHEMISTRY

C	Cr	Ni	Mo	Mn	Si	P	S	Cu	N
.03	20.5	13.3	3.10	1.7	.50	.020	.010	.10	.06

FERRITE CONTENT 5-15 WRC 1992

TYPICAL MECHANICAL PROPERTIES (as welded all weld metal)

TENSILE STRENGTH	87,500 PSI
YIELD STRENGTH	60,500 PSI
ELONGATION IN 2"	38%

RECOMMENDED WELDING PARAMETERS

DIAMETER	AMPERAGE	
	FLAT	VERTICAL & OVERHEAD
3/32"	70-85	65-75
1/8"	85-110	80-90
5/32"	110-140	100-120
3/16"	120-160	110-130

STANDARD PACKAGING

- 3/32" - 8 lb. can, 48 lb. Carton
- 1/8", 5/32", 3/16" - 10 lb. Can, 60 lb. Carton

7/1/09

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Dr.
 Fenton, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

Midalloy