

MIDALLOY MASTERCOR ENiFe-CI FLUX-CORED WIRE

CLASSIFICATION

- MIDALLOY MASTERCOR ENiFe-CI flux-cored wire conforms to AWS/SFA 5.15 classification ENiFeT3-CI
- UNS# W82032

DESCRIPTION

- MIDALLOY MASTERCOR ENiFe-CI is a gasless flux-cored nickel alloy cored wire designed for welding cast iron.
- This wire has as high a deposition rate as solid wire, but with lower amperage, thus less heat input.

APPLICATIONS

- MIDALLOY MASTERCOR ENiFe-CI is used in the flat position for joining, building-up, and repairing cast iron parts and castings.
- This product provides a hard deposit that is not easily machinable, but can be used for multiple layers.
- When welding cast iron, always preheat and slow cool.
- Convex beads are desired, and peening is necessary after each weld.

TYPICAL CHEMISTRY

C	Fe	Ni	Mn	Si	S	Cu	Al	Others
0.90	Bal	55.0	3.75	0.35	.001	0.10	0.35	<1.0

MECHANICAL PROPERTIES

TENSILE STRENGTH	80,000 PSI Min.
ELONGATION	30% Min.

WELDING PARAMETERS

SIZE	VOLTS	AMPS	STICKOUT	SHIELDING GAS
.045"	25-26	170-220	3/8" – 1/2"	None Required
1/16"	26-27	220-270	3/8" – 1/2"	None Required

STANDARD PACKAGING

- .045" Dia. 33 lb. spool
- 1/16" Dia. 50 lb. spool

4/15/19

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 St. Louis, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

