

MIDALLOY ER80S-Ni2 WELDING WIRE

CLASSIFICATION

- AWS A5.28 Class ER80S-Ni2 / ASME SFA 5.28 Class ER80S-Ni2 (UNS K21240), EN10204 and EN 440 G2 Ni2, EN 1688 W2 Ni2

DESCRIPTION

- MIDALLOY ER80S-Ni2 is a copper free bare wire used for GMAW and GTAW welding.
- ASME Section IX F#6 A#10

APPLICATION

- MIDALLOY ER80S-Ni2 welding wire is used for Tig root passes or Tig & Mig joining for low-temperature, fine-grained steels. These alloys have higher strength and require good toughness at temperatures as low as -60°F.

TYPICAL CHEMISTRY

C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu
.11	1.02	.58	.012	.010	2.35	.04	.01	.002	.14

TYPICAL MECHANICAL PROPERTIES PWHT

TENSILE STRENGTH	88,000 PSI (620 KPA)
YIELD STRENGTH	71,950 PSI (510 KPA)
ELONGATION IN 2"	25%
CHARGE IMPACT @ -60°C	38 ft. lbs. Average 50 joules

RECOMMENDED WELDING PARAMETERS

PROCESS	DIA. OF WIRE	AMPERAGE	VOLTAGE	GAS/FLUX
GTAW	1/16"	50-120	7-13	Ar
	3/32"	120-200	10-16	Ar
	1/8"	150-220	12-18	Ar
GMAW (MIG) SHORT ARC	.035"	90-160	14-20	CO ₂
	.045"	120-200	16-20	CO ₂ or 75 Ar/25 CO ₂
	1/16"	-	-	CO ₂ or 75 Ar/25 CO ₂
GMAW (MIG) SPRAY TRANSFER	.035"	180-230	25-28	98 Ar/2 O ₂ or
	.045"	250-350	25-30	75 Ar/25 CO ₂ or
	1/16"	280-400	26-36	90 Ar/10 CO ₂

STANDARD PACKAGING

- MIG 33 lb. Spool
- TIG 10 lb. Tubes / 60 lb. Cartons

6/21/19

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
 630 Axminister Drive
 St. Louis, MO 63026 • 636-349-6000 • 800-776-3300
 Fax 636-349-2240

