

## MIDALLOY ERNiCu-7 (FM60) BARE WIRE

### CLASSIFICATION

- AWS 5.14 Class ERNiCu-7 / ASME SFA 5.14 Class ERNiCu-7

### DESCRIPTION

- MIDALLOY ERNiCu-7 nickel-copper alloy bare wire is used for GMAW, GTAW, and SAW welding.

### APPLICATIONS

- MIDALLOY ERNiCu-7 is used for joining base materials such as UNS number N04400, number N04405, and number N05500. This includes ASTM grades such as B127, B163, B164, B165, and B564.
- This alloy can also be used for dissimilar welding applications using various nickel-copper alloys to nickel 200 and to copper-nickel alloys.
- This alloy can be used to overlay over carbon steel, provided a buffer layer of ERNi-1 is used for the first layer.

### TYPICAL CHEMISTRY

C	Mn	Fe	P	S	Si	Cu	Ni	Al	Ti
.05	3.53	.53	.004	.002	.87	Bal.	65.3	.02	2.20

### TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	75,000 PSI
YIELD STRENGTH	52,000 PSI
ELONGATION	34%

### RECOMMENDED WELDING PARAMETERS

(See attached)

### STANDARD PACKAGING

- TIG 10 lb. tube / 60 lb. carton
- MIG 30 lb. spool
- SUB-ARC 60 lb. coil

10-15-2010

*The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.*

Office and Corporate Warehouse  
 630 Axminister Drive  
 St. Louis, MO 63026 • 636-349-6000 • 800-776-3300  
 Fax 636-349-2240



TYPICAL WELDING PARAMETERS FOR NICKEL ALLOYS

**GMAW (SHORT CIRCUITING MODE)**

WIRE DIA.	AMPERAGE	VOLTAGE	WIRE SPEED, IN./MIN.	JOINT THICKNESS IN.	GAS
.035"	70-90	18-20	150-200	.050-3/16	75Ar/25He
	70-90	17-20	150-200	.050-3/16	90He/7.5Ar/2.5Co2
	70-90	17-20	150-200	.050-3/16	69Ar/30He/1Co2
.045"	75-160	19-22	175-225	1/8-3/4	75Ar/25He
	75-160	19-22	175-225	1/8-3/4	90He/7.5Ar/2.5Co2
	75-160	18-22	175-225	1/8-3/4	69Ar/30He/1Co2

**GMAW (SPRAY TRANSFER MODE)**

.045"	190-250	30-32	300-350	3/8 and UP	100Ar
-------	---------	-------	---------	------------	-------

**GMAW (PULSED CURRENT MODE)**

.045" peak	120-150 250-300	18-20	175-225	1/8-3/4	75Ar/25He
peak	120-150 250-300	18-20	175-225	1/8-3/4	69Ar/30He/1Co2

**GTAW (TIG)**

JOINT THICKNESS IN.	TUNGSTEN ELECTRODE DIA. IN.	FILLER WIRE DIA. IN.	AMPERAGE	VOLTAGE	GAS
.030 to 1/16	1/16	1/16	35-60	9-12	100Ar
1/16 to 1/8	1/16 to 3/32	1/16 or 3/32	50-95	9-12	100Ar
1/8 to 1/4	3/32 or 1/8	3/32 or 1/8	75-150	10-13	100Ar
1/4 and up	3/32 or 1/8	3/32 or 1/8	95-200	10-13	100Ar

**SAW (SUBMERGED ARC)**

WIRE DIA.	AMPERAGE	VOLTAGE	
3/32"	275-350	28-30	Suitable flux
1/8"	350-450	29-32	Suitable flux

**SMAW (COATED ELECTRODES)**

DIA. & LENGTH	AMPERAGE/FLAT	AMPERAGE/ VERT. & OVERHEAD	VOLTAGE
3/32" x 12"	70-85	65-75	24-28
1/8" x 14"	85-110	80-90	26-30
5/32" x 14"	110-140	100-120	28-32
3/16" x 14"	120-160	110-130	28-32

*The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.*